ISSUED BY VIENNA WOODS LTD, 7 AUGUST 2026. TECHNICAL MAPPING PER VW-FIRE-001 (EDDY, 7 AUGUST 2026); WORDING CLEARED PER VW-FIRE-001-A (ADRIAN, 7 AUGUST 2026).

VIENNA WOODS
2 Roxburgh Street · Newmarket · Auckland · 0800 843 662 · viennawoods.co.nz · support@viennawoods.co.nz

Document **VW-DS-UN-001**
Version **1.4**
Issued **11 November 2026**
Supersedes — v1.3 (2 October 2026)

PRODUCT DATA SHEET

Unfinished Oak 190 × 2200 mm

A 15 mm engineered European oak plank with a 4 mm oak wear layer over a multi-ply core, supplied raw — no stain, oil or lacquer — so the colour, texture and sheen are set when it is finished, on site or off site. The same board specification as Vienna Woods' Petit Château collection, without the factory finish.

01 Construction

Species	European oak
Origin	Engineered overseas to Vienna Woods' specification
Board	15 mm engineered board
Wear layer	4 mm European oak
Core	Multi-ply (eucalyptus / birch)
Finish	Supplied unfinished — no stain, oil or lacquer. Finished by others, on site or off site.
Texture	Brushed
Grade	Feature
Edge	0.5 mm micro-bevel
Profile	Tongue and groove
Installation	Full-spread adhesive, glue-down

COATING REQUIRED BEFORE USE

VW Unfinished must be finished with a suitable floor coating before the floor is put into use.

As a natural timber product, some variation in colour and grain between boards is normal.

02 Formats and sizes

FORMAT	SIZE	GRADE	AVAILABILITY
Feature plank	190 × 2200 × 15/4 mm	Feature	In stock — 2.508 m² per carton

03 Certification

Forest certification	Made by a mill that holds a current FSC Chain of Custody certificate (FSC 100%), current to 27 October 2030. Vienna Woods does not hold a Chain of Custody certificate and cannot pass an FSC claim to the finished floor.
Formaldehyde emissions	The plywood core is certified to CARB Phase 2 and US EPA TSCA Title VI, current to 12 December 2026. The certification is held on the plywood veneer core, not on the finished floor.

Certificates are available to specifiers on request. Certificate numbers and manufacturer identities are not published.

04 New Zealand Building Code

Installed and maintained in accordance with Vienna Woods' requirements, this product will assist with meeting the performance clauses below. Whether a clause is satisfied on a given project depends on the design, the build-up and the occupancy, and remains the specifier's determination against the Building Code.

> **WHO DETERMINES COMPLIANCE**
>
> Vienna Woods states the properties of its own products and the route by which those properties are established. Whether a particular building complies with the Building Code is a determination for the designer, the fire engineer and the building consent authority on that project. This material is general information current at the date shown. It is not a compliance determination and it is not a substitute for project-specific advice. Verify against the current text of the Building Code, C/AS2 and the Building Product Specifications at building.govt.nz.

CLAUSE	POSITION AND LIMITS
B2.3.1(b) Durability	A full-spread adhesive-fixed floor covering is moderately difficult to replace, which is the B2.3.1(b) case. Supplied with a 20-year residential / 5-year commercial structural warranty. Which B2 durability period applies (50 / 15 / 5 years) depends on how the floor sits in the building and remains the specifier's determination.
C3.4(b) Fire — floor surfaces	Vienna Woods engineered timber flooring is a wood product within Table 8.1.2.1 of the Building Product Specifications (1st edition Amendment 1, 2 April 2026) and takes the generic critical radiant flux of 2.2 kW/m². Where NZBC C/AS2 (Second edition, 28 July 2025) applies, that value is assessed against Table 4.12.3.1. No ISO 9239-1:2010 test report is required to establish it. This product is supplied unfinished and is finished by others, on site or off site. Vienna Woods' statement is made about the board as supplied. Installation requirement. The generic critical radiant flux in Table 8.1.2.1 is available to a coated board only where the applied coating is not more than 0.4 mm thick and not more than 100 g/m² (Building Product Specifications, paragraph 8.1.2.1(a)(i)). When this floor is finished, on site or off site, the coating system must be within those limits for the generic value to apply to the finished floor. Confirming this is the responsibility of the party specifying or applying the finish, from that coating manufacturer's technical data. Vienna Woods holds no Group Number test. Where 2.2 kW/m² is sufficient, and where it is not. In buildings where care or detention is provided, sleeping areas and exitways require a critical radiant flux of 4.5 kW/m² where the building is unsprinklered (NZBC C3.4(b); C/AS2 Table 4.12.3.1, risk group SI). The generic 2.2 kW/m² value does not meet that requirement. Those spaces require a project-specific ISO 9239-1:2010 test report or a sprinklered design. Everywhere else in Table 4.12.3.1 — exitways, non-sleeping firecells accommodating more than 50 people, and all other occupied spaces — 2.2 kW/m² meets the requirement. Clause C3.4 of the New Zealand Building Code does not apply to detached dwellings, to the inside of household units in multi-unit dwellings, or to outbuildings and ancillary buildings. There is therefore no critical radiant flux requirement for a floor inside a household unit. This describes the scope of the Building Code requirement only. It is not a statement about the fire performance or the

CLAUSE	POSITION AND LIMITS
	fire safety of the floor, and it does not affect any other Building Code requirement, any requirement of a fire design, or any requirement of an insurer. Multistorey buildings where the floor is a fire separation. C/AS2 paragraph 4.12.3.3 sets an additional requirement where floors in multistorey buildings are fire separations and the flooring material is a wood product: the flooring material must be not less than nominally 20 mm thick, or the floor assembly must achieve an FRR of -/30/30 when exposed to fire from the flooring side. Vienna Woods' stocked boards are 14–15 mm. The 20 mm Distilled build is made to order. Whether this paragraph applies to a thin timber overlay bonded to a separating floor — rather than to structural floor decking that forms the separation itself — is a determination for the project's fire engineer and the building consent authority. Vienna Woods does not make that determination. Where a floor is or may be a fire separation, confirm the requirement before specifying.
D1.3.3(d) · E3.3.3 Slip · internal moisture	This product is supplied unfinished. Slip resistance (D1) and the impervious-surface requirement for internal moisture (E3) are properties of the finish applied after supply, on site or off site, not of the board as supplied. Meeting them is the responsibility of the party specifying or applying the finish, from that coating system's own test data.
F2.3.1 Hazardous building materials	NZBC F2 sets no numeric emission limit and F2/VM1 adopts no test method for it. See the certification section above for the position on this collection.

> **WHERE THE CLAUSE TABLE LIVES**
>
> The Building Code clause positions summarised here are stated in full, once, in the Vienna Woods Timber Overlay Flooring System Product Technical Statement. Where this sheet and the Product Technical Statement differ, the Product Technical Statement governs.

Floors and wall linings are different systems

Floors and wall linings are rated under different systems and the two cannot be converted into one another. Floor surface materials are assessed under NZBC C3.4(b) by critical radiant flux in kW/m², tested to ISO 9239-1:2010. Wall and ceiling linings are assessed under NZBC C3.4(a) by Material Group Number, tested to ISO 9705. A floor's critical radiant flux cannot be expressed as a Group Number, and a Group Number cannot be expressed as a critical radiant flux.

These boards may be used as an interior wall or ceiling lining. Where they are, the fire requirement is a Material Group Number under NZBC C3.4(a) (ISO 9705) — a different measure from the floor critical radiant flux above, which cannot be converted into it. The Group Number is the specifier's determination.

Wall lining is not the use for which this product is primarily supplied. Fixing, substrate, cavity and fire-stopping details are outside Vienna Woods' scope and are the designer's responsibility.

G6 Airborne and impact sound

G6 applies to floors between occupancies in multi-unit residential buildings and requires airborne (STC) and impact (IIC) ratings for the floor as built. No floorboard or underlay carries a rating on its own. A timber floor is generally taken to G6 compliance as an Alternative Solution, with the build-up designed and verified by an acoustic engineer. Vienna Woods holds no IIC or impact-sound test report for any build-up.

05 Installation, maintenance and limits

Installation

Follow the Vienna Woods installation and levelling guides — acclimatisation, expansion gaps and vapour barriers on concrete. Full-spread adhesive fixing with Parabond Parquet 440; substrate flat within 3 mm over a 3 m straightedge. Use D3-rated PVA at joins and a flexible perimeter sealant within 1.5 m of sanitary fixtures, per the

Limitations

Not suitable for permanent wet areas (bathrooms containing a shower or bath, saunas), garages, commercial kitchens, or any exterior application. Colour change from UV exposure is normal in timber; mitigate with blinds or UV-filtering glazing. VW Unfinished must be finished with a suitable floor coating before the floor is put into use.

Vienna Woods wet-area detail. Only qualified installers should fit these products.

Suitable over underfloor heating, subject to a maximum surface temperature of 27 °C.

Maintenance

Use cleaning and maintenance products recommended by the maker of the finish applied. Maintain relative humidity between 40–60% where practical. Improper maintenance may affect durability.

Warnings and known risks

Excess moisture may cause cupping, swelling or delamination. Incorrect subfloor preparation may compromise performance.

Warranty

20 years residential / 5 years commercial, structural integrity, on Vienna Woods' own-brand engineered timber flooring (VW-WTY-001). Issued in addition to, and not in place of, the customer's rights under the Consumer Guarantees Act 1993.

There is no surface-finish warranty. This product is supplied unfinished; the finish applied after supply, on site or off site, and its performance are the responsibility of the party who specifies or applies it.

06 Supporting documents

- **Vienna Woods Timber Overlay Flooring System — Product Technical Statement** — the Building Code clause table in full
- **Vienna Woods BPIR (VW-BPIR-001 v3.8)** — per-collection construction, certification and compliance
- **Vienna Woods Installation Guide and Levelling Instructions**
- **Parabond Parquet 440 technical data sheet** (DL Chemicals)
- **Vienna Woods Product Warranty — Engineered Timber Flooring (VW-WTY-001 v3.3)**

None of the products covered by this statement is subject to a warning or ban under section 26 of the Building Act 2004.

Vienna Woods Limited, 2 Roxburgh Street, Newmarket, Auckland 1023 · NZBN 9429049033199. Vienna Woods designs and specifies these collections and has them produced to its specification under contract manufacture; Vienna Woods is the manufacturer for the purposes of this statement. · Masterspec work section **6312VW**.
Certificate positions read from the Vienna Woods certificate register on 11 November 2026 and re-read on every reissue of this sheet. Issued in addition to, and not in place of, the customer's rights under the Consumer Guarantees Act 1993.